



Technical Data sheet

Product Name : GD-115-15 (Solid)

Stock Number : GD-2023-013

Technical Analysis

1. Colour	:	Black
2. Appearance	:	Solid
3. Penetration	:	12-20mm
4. Softening point °C	:	114-117 °C
5. Specific gravity at 25°C	:	0.96
6. Viscosity of 50% in MTO	:	180-190 sec
7. Viscosity of 50% in xylene	:	130-140 sec
8. Finish	:	Smooth
9. Surface dry in MTO	:	60 min(approx)
10. Surface dry in xylene	:	10-12 min
11. Solubility	:	MTO, TO & Xylene, etc.

Main Inspect Verifier : Manager QC

Note:

- All the parameters of GD-115-15 are according to customer requirement
- Product Specification is subject to amendment and may change over time



FACTORY

467/3, Naigaon Road, Shinde,
Nashik - 422 102.



OFFICE

Pritam Complex, Amrutdham,
Near East End Hotel, Hanuman Nagar,
Panchavati, Nashik - 422 003.



GSTIN : 27AAVFG1857A1ZA

goldenexusllp@gmail.com