



Technical datasheet

Oxidised bitumen 140, (GD-140)

Stock No: GD-2023-102

Technical Analysis

1. Product Name	:	GD-140
2. Stock No.	:	GD-2023-102
3. Colour	:	Black
4. Appearance	:	Solid
5. Softening Point of Bitumen	:	141.5°C
6. Viscosity	:	280 sec
7. Specific Gravity @ 30°C	:	0.98
8. Solubility	:	MTO, Xylene etc
9. Surface dry	:	8 mins.
10. Complete dry	:	18 mins.

Main Inspect Verifier : Manager QC

Note:

- All the parameters of GD-140 are according to customer requirement.
- Product Specification is subject to amendment and may change over time.



FACTORY

467/3, Naigaon Road, Shinde,
Nashik - 422 102.



OFFICE

Pritam Complex, Amrutdham,
Near East End Hotel, Hanuman Nagar,
Panchavati, Nashik - 422 003.



GSTIN : 27AAVFG1857A1ZA

goldenexusllp@gmail.com