



Technical datasheet

GD-140, (50% solid bitumen in xylene)

Stock No: GD-2023-102

Batch: GD140-2024-B3

Technical Analysis

1. Product Name	:	GD-140
2. Stock No.	:	GD-2023-102
3. Batch no.	:	GD140-2024-B3
4. Solvent	:	Xylene
5. Solvent (%)	:	50%
6. Solid Content	:	50%
7. Appearance	:	Smooth Liquid
8. Finish	:	Glossy
9. Softening Point of GD-140	:	140.3°C
10. Viscosity @ 30°C	:	100-110 sec
11. Specific Gravity @ 30°C	:	0.96
12. Surface dry	:	6-8 mins.
13. Complete Dry	:	15 mins.

Main Inspect Verifier : Manager QC

Note:

- All the parameters of GD-140 are according to customer requirement.
- Product Specification is subject to amendment and may change over time.
- Shake well before use.



FACTORY

467/3, Naigaon Road, Shinde,
Nashik - 422 102.



OFFICE

Pritam Complex, Amrutdham,
Near East End Hotel, Hanuman Nagar,
Panchavati, Nashik - 422 003.



GSTIN : 27AAVFG1857A1ZA

goldenexusllp@gmail.com